



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B05D 7/24, C23C 16/44	A1	(11) International Publication Number: WO 97/04885 (43) International Publication Date: 13 February 1997 (13.02.97)
(21) International Application Number: PCT/US96/12288 (22) International Filing Date: 25 July 1996 (25.07.96) (30) Priority Data: 08/508,278 27 July 1995 (27.07.95) US (71) Applicant: BATTELLE MEMORIAL INSTITUTE [US/US]; Pacific Northwest Laboratories, Intellectual Property Ser- vices, 902 Battelle Boulevard, P.O. Box 999, Richland, WA 99352 (US). (72) Inventors: AFFINITO, John, D.; R.R. 4, Box 4485 #F, Clodfelter Road, Kennewick, WA 99336 (US). GROSS, Mark, E.; 50 Deseret Drive, Pasco, WA 99301 (US). ZIMMERMAN, Paul, W.; 4720 West Janet Road, Pasco, WA 99301 (US). (74) Agent: ZIMMERMAN, Paul, W. (K1-53); Battelle Memorial Institute, Pacific Northwest Laboratories, Intellectual Prop- erty Services, 902 Battelle Boulevard, P.O. Box 999, Rich- land, WA 99352 (US).		(81) Designated States: BR, CA, CN, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: VACUUM FLASH EVAPORATED POLYMER COMPOSITES (57) Abstract A method for fabrication of polymer composite layers in a vacuum is disclosed. More specifically, the method of dissolving salts in a monomer solution, vacuum flash evaporating the solution, condensing the flash evaporated solution as a liquid film, and forming the condensed liquid film into a polymer composite layer on a substrate is disclosed.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic			SE	Sweden
CG	Congo	KR	Republic of Korea	SG	Singapore
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LR	Liberia	SZ	Swaziland
CS	Czechoslovakia	LT	Lithuania	TD	Chad
CZ	Czech Republic	LU	Luxembourg	TG	Togo
DE	Germany	LV	Latvia	TJ	Tajikistan
DK	Denmark	MC	Monaco	TT	Trinidad and Tobago
EE	Estonia	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	UG	Uganda
FI	Finland	ML	Mali	US	United States of America
FR	France	MN	Mongolia	UZ	Uzbekistan
GA	Gabon	MR	Mauritania	VN	Viet Nam

VACUUM FLASH EVAPORATED POLYMER COMPOSITES

5

FIELD OF THE INVENTION

The present invention relates generally to a method for fabrication of polymer composite layers in a vacuum.

10 More specifically, the invention relates to dissolving salts in a monomer solution, flash evaporating the solution, and forming the evaporated solution into a polymer composite layer on a substrate.

BACKGROUND OF THE INVENTION

15 Laminate structures having at least one polymer layer have been shown to be useful in a wide variety of applications including, but not limited to, electronic devices, such as circuit elements and electrochromic devices, packaging materials, and solar reflectors. Also, polymer layers which also contain ions or salts have been
20 shown to exhibit characteristics not present in simple polymer layers. Thus, polymer layers containing ions or salts, or composite polymers, may exhibit a variety of characteristics, such as increased ion conductivity, which may render them superior to polymers which do not include
25 ions or salts, for specific uses.

Several techniques are known in the art for the mass production of polymer and polymer composite layers under vacuum conditions. For example, polymer and polymer composite layers have been produced by methods including,
30 but not limited to, extrusion and monomer spreading apparatus such as roll coaters, gravure roll coaters, wire wound rods, doctor blades and slotted dies, wherein a liquid monomer or a liquid monomer solution containing ions or salts is deposited onto a substrate and cured.

- 2 -

Vacuum flash evaporation of monomer fluids has also been shown to be a useful process for creating thin polymer layers in laminate structures. However, those skilled in the art have avoided the use of the vacuum flash evaporation method for the formation of polymer composite layers. Generally, the temperature required to evaporate salts is too high to permit the inclusion of salts in the evaporation of monomers according to the flash evaporation method. For example, U.S. Patent 4,954,371 incorporated herein by reference, "Flash Evaporation of Monomer Fluids" discloses a method for continuously supplying a polymerizable and/or cross linkable material at a temperature below the decomposition and polymerization temperature of the material. The material is atomized to droplets having a particle size ranging from about 1 to about 50 microns. The droplets are then vaporized, under vacuum, by contact with a heated surface above the boiling point of the material, but below the temperature which would cause pyrolysis. The method teaches that by condensing the vapor onto a substrate as a liquid, the material may then be polymerized or cross linked, allowing the formation of very thin polymer layers in a laminate structure.

The use of the vacuum flash evaporation method provides a polymer layer with certain advantages over other methods of forming polymer layers, including, but not limited to the ability to create more uniform and thinner polymer layers, a reduction of trapped gas under the polymer layer, greater density within the polymer layer and a smoother finished surface.

It is therefore of great interest to those skilled in the art to have a method for forming polymer composite layers including ions or salts and having the advantages of the vacuum flash evaporation method.

SUMMARY OF THE INVENTION

The present invention relies on the unexpected discovery that, when fully solvated, salts dissolved in monomer solutions may be evaporated along with the monomer according to the vacuum flash evaporation method and thereby used to form composite polymer layers under vacuum. More specifically, according to the present invention, a salt is first fully solvated in a monomer solution. The mixture is then used to form polymer composite layers according to the vacuum flash evaporation method. Also, a combination of solvents, photo-curing agents, adhesion promoters or slip agents may be added to the monomer/salt mixture prior to flash evaporation.

DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

In a preferred embodiment of the present invention, a salt is dissolved or solvated in a polymerizable and/or cross linkable material, typically a monomer solution containing at least one monomer in a liquid state, to form a polymerizable composite material. The salt may be any ionic compound wherein the ions can be made to dissociate in the solution including but not limited to binary and complex salts. As used herein, the term complex salt is any salt having more than two elements. Other constituents may be added as desired, for example, a solvent may be added to aid in solvation of the salt within the monomer solution, an adhesion promoter to aid in the formation of the composite polymer on a substrate, or a photoinitiator to aid in the polymerization of the composite polymer. Once the salt is dissolved or solvated, the polymerizable composite material, is processed according to the vacuum flash evaporation process whereby the polymerizable composite

material is continuously supplied as a substantially uniform vapor under vacuum. The method thus allows the polymerizable composite material to be deposited on a substrate under vacuum to form a composite polymer layer.

5 The polymerizable composite material is continuously supplied at a temperature below the decomposition and polymerization temperature of the material. The material is atomized to droplets having a particle size ranging from about 1 to about 50 microns, or
10 smaller. Atomization is typically done using an ultrasonic horn. Atomization may also be done electrostatically. Electrostatic atomization at high voltages from about 1 kV to about 20 kV may result in more uniform droplet size and improved vaporization.
15 Additionally, a charge may be imparted to droplets that would be attracted to the heated surface maintained at an opposite charge thereby improving the throughput of droplets. The droplets are then vaporized by contact with a heated surface above the boiling point of the material,
20 but below the temperature which would cause pyrolysis. The vapor is then brought into contact with a substrate, where the material condenses as a liquid film and is then polymerized or cross linked, allowing the formation of a composite polymer layer under vacuum.

25 It is preferred that the salt be solvated in the monomer solution to the maximum extent possible prior to flash evaporation. The more complete the solvation, the greater the amount of the salt, or ions of the salt, will be available to be evaporated along with the monomer solu-
30 tion, and thereby formed into the polymer composite layer. Also, the relative concentration of salt to monomer can be varied by varying the amount of salt in the monomer solution. Beginning with no salt added to the monomer, salt may be added to any desired concentration up to saturation
35 of the monomer solution.

EXAMPLES

An experiment was done wherein 150 mL of polyethyleneglycol diacrylate, 150 mL of polyethyleneglycol methyl ether, 15 mL of acrylic acid
5 adhesion promoter, 30 mL of commercially available Darocure 4265 photoinitiator available from CIBA/GEIGY Inc., Hawthorn, NY, and 20 g of LiCF_3SO_3 was mixed until the LiCF_3SO_3 was completely solvated in the mixture. The mixture was then formed into a multilayer lamellar
10 composite in accordance with the vacuum flash evaporation method of the present invention. The laminar composite consisted of a layer of the composite polymer material placed in between two layers of aluminum in an interdigitated capacitor structure where all layers were
15 vacuum deposited. The multilayer lamellar composite was then tested with a standard voltmeter and exhibited a conductance consistent with electrolyte material, indicating the inclusion of the ions of the LiCF_3SO_3 salt in the polymer.

20 While a preferred embodiment of the present invention has been shown and described, it will be apparent to those skilled in the art that many changes and modifications may be made without departing from the invention in its broader aspects. The appended claims are
25 therefore intended to cover all such changes and modifications as fall within the true spirit and scope of the invention.

CLAIMS

We claim:

1. A method for supplying a uniform vapor of a polymerizable composite material in vacuum, said method
5 comprising:

a) dissolving a salt in a monomer to form said composite material,

b) supplying a liquid flow of said composite material into a vacuum environment at a temperature below
10 both the decomposition temperature and the polymerization temperature of the composite material,

c) atomizing the liquid flow into a flow of liquid droplets; and

d) vaporizing said liquid droplets by
15 causing said droplets to contact a heated surface which is maintained at a temperature at or above the boiling point for said composite material, but below the temperature at which said droplets would undergo pyrolysis before vaporizing.

20 2. The method as recited in claim 1, used for depositing onto a substrate in a vacuum environment a layer of polymerizable composite material, said method further comprising the steps of:

e) maintaining at least a portion of said
25 substrate at a temperature which is below the boiling point of said composite material and in a region which is at a lower pressure than said vaporized composite material, to provide a positive flow of vaporized composite material toward said substrate; and

30 f) directing the flow of said vaporized composite material onto said substrate.

- 7 -

3. The method as recited in claim 2, wherein said material is chemically unstable at or below its boiling point.

4. The method as recited in claim 1, wherein
5 atomizing comprises:

ultrasonically vibrating a device and dispersing the composite material supplied to the device in droplets.

5. The method as recited in claim 4, wherein
10 dispersing comprises:

coating an end surface at a tip of the device with said composite material;

ultrasonically vibrating said end surface thereby dispersing said droplets from the periphery of the
15 end surface.

6. The method as recited in claim 1, wherein atomizing comprises:

electrostatically spraying said composite
20 material.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 96/12288

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B05D7/24 C23C16/44

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B05D C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO,A,87 07848 (SPECTRUM CONTROL INC) 30 December 1987 see the whole document ---	1
A	US,A,4 696 719 (BISCHOFF GREGG C) 29 September 1987 see the whole document -----	4,5

☐

Further documents are listed in the continuation of box C.

☒

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

19 November 1996

Date of mailing of the international search report

28. 11. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Brothier, J-A

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/12288

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-8707848	30-12-87	DE-A- 3786063 EP-A- 0270656 JP-B- 2530350 JP-T- 63503552 US-A- 4954371	08-07-93 15-06-88 04-09-96 22-12-88 04-09-90
US-A-4696719	29-09-87	NONE	

BEST AVAILABLE COPY

THIS PAGE BLANK (USPTO)